

AMENDMENTS TO THE SPECIFICATION

In the specification, page 6, paragraph beginning on line11:

Thereafter, as shown in FIG. 3D, a metal layer 115, e.g., a deposition layer of gold/chrome, is deposited with a thickness of approximately 1.5-2.5 μm using DC magnetron sputtering to form a CPW signal line and a CPW ground plane.